

STANDARD FLY ASH CERTIFICATE



FINAL
Prior Reports: None

Flyash Australia Pty Ltd
ABN 68 002 840 271
Head Office
C/- Lindfield Corporate Centre
Suite 18, 12 Tryon Road
Lindfield NSW 2070
Tel : (02) 9413 8422
Fax: (02) 9413 84.32
www.flyashaustralia.com.au

Certificate Number: CERT210152
Issued: 18 January 2021

Product being certified: Mt Piper Monthly Grab Fly Ash
Product sample date: 01-Dec-2020
Sample Identification: Sample Code: 20120174
Source Power Station: Mount Piper Power Station
Sample Condition: Tested as Received. Testing Commenced on 04-Dec-2020
Certifying Laboratory: Cement Australia - Darra Laboratory,
18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

Test	Moisture %	Fineness @ 45 micron % Passed	Loss on Ignition %	Sulfuric Anhydride %	Available Alkali %	Chloride Ion %	Chemical Composition %
Result	0.1	86	1.4	< 0.1	n/a	< 0.001	94.1
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement %	Strength Index 7 Day Acc. %	Reference Cement Details
Result	2.14	95	99	Identification:: 20120975 Source: Goliath GP
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP
AS 3582.1	-	-	75% Minimum	Sample Date: 31-Dec-20

Additional Testing - Oxides

Test	CaO by XRF %	SiO ₂ by XRF %	Al ₂ O ₃ by XRF %	Fe ₂ O ₃ by XRF %	SO ₃ by XRF %	MgO by XRF %	Na ₂ O by XRF %
Result	0.2	66.1	25.2	2.8	< 0.1	0.2	0.39
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K ₂ O by XRF %	SrO by XRF %	TiO ₂ by XRF %	P ₂ O ₅ by XRF %	Mn ₂ O ₃ by XRF %	Total Alkali (NaEQ) %
Result	2.65	<0.1	0.9	0.3	< 0.1	2.13
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special	Grade 1	Grade 2
	X	

Approved Signatory



A Prem
Signatory - Cement Australia
Chemical Testing
Construction Materials Testing

Accredited for compliance with ISO/IEC
17025 - Testing. The results of the tests,
calibrations and/or measurements included in
this document are traceable to
Australian/national standards.

Cement Australia - Darra Laboratory
NATA Accredited Laboratory Numbers
187 188



ACCREDITED FOR
**TECHNICAL
COMPETENCE**

Notes:

