# STANDARD FLY ASH CERTIFICATE

**FINAL**

**Prior Reports: None**

**Flyash Australia Pty Ltd**
ABN 68 002 840 271
P.O. Box 190
Eastwood NSW 2122
Email: contact@flyash.com.au
www.flyashaustralia.com.au

**Certificate Number:** CERT265063
**Issued:** 20 August 2026

| | |
|---|---|
| **Product being certified:** | Bayswater Monthly Grab Fly Ash |
| **Product sample date:** | 15-May-2026 |
| **Sample Identification:** | Sample Code: 26051387 |
| **Source Power Station:** | Bayswater Power Station |
| **Sample Condition:** | Tested as Received. Testing Commenced on 28-Jul-2026 |
| **Certifying Laboratory:** | Cement Australia - Darra Laboratory, 18 Station Avenue, Darra Queensland 4076 Australia. |

**Test results in this report are only relevant to the sample tested.**

## Test Results

| Test | Moisture % | Fineness @ 45 micron % Passed | Loss on Ignition % | Sulfuric Anhydride % | Available Alkali % | Chloride Ion % | Chemical Composition % |
|---|---|---|---|---|---|---|---|
| Result | < 0.1 | 87 | 0.6 | < 0.1 | Not Tested | < 0.001 | 97 |
| Test Method | AS 3583.2 | AS 3583.1 | AS 3583.3 | AS 2350.2 | AS 3583.12 | AS 3583.13 | AS 2350.2 |
| AS/NZS 3582.1 | 0.5 % Maximum | 75% Minimum | 4.0 % Maximum | 3.0 % Maximum | - | 0.1 % Maximum | 70% Minimum |

| Test | Relative Density | Relative Water Requirement % | Strength Index 7 Day Acc. % |
|---|---|---|---|
| Result | 2.11 | 96 | 95 |
| Test Method | AS 3583.5 | AS 3583.6 | AS 3583.6 |
| AS/NZS 3582.1 | - | - | 75% Minimum |

Reference Cement Details
Identification:: 26080104
Source: GP
Product Type: Type GP
Sample Date: 4-Jun-26

### Additional Testing - Oxides

| Test | CaO by XRF % | $SiO_2$ by XRF % | $Al_2O_3$ by XRF % | $Fe_2O_3$ by XRF % | $SO_3$ by XRF % | MgO by XRF % | $Na_2O$ by XRF % |
|---|---|---|---|---|---|---|---|
| Result | 0.4 | 76.6 | 17.1 | 3.1 | < 0.1 | 0.4 | 0.10 |
| Test Method | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 |

| Test | $K_2O$ by XRF % | SrO by XRF % | TiO2 by XRF % | $P_2O_5$ by XRF % | $Mn_2O_3$ by XRF % | Total Alkali (NaEQ) % |
|---|---|---|---|---|---|---|
| Result | 0.87 | <0.1 | 0.6 | <0.1 | < 0.1 | 0.68 |
| Test Method | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 | AS 2350.2 |

**This sample conforms to the material requirements as presscribed in Table 1 of AS 3582.1**

| Special | Grade 1 | Grade 2 |
|---|---|---|
| | X | |

**Approved Signatory**

J Ventura
Signatory - Cement Australia
Chemical Testing
Construction Materials Testing

Accredited for compliance with ISO/IEC 17025 - Testing
NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates.

**Laboratory accreditation number: 187**

NATA
WORLD RECOGNISED ACCREDITATION

**Notes:**

2 6 0 5 1 3 8 7

C E R T 2 6 5 0 6 3

This test report shall not be reproduced except in full, without written approval from Flyash Australia.